

XL-1041 Silicone Styrene Acrylic Emulsion

Features

- Shell and nuclear silicone styrene acrylic copolymer.
- Excellent water white resistance, excellent anti-yellowing performance, high dirt & block resistance.
- Environment friendly, no formaldehyde, APEO free.

Product data

Appearance	Milky white liquid with blue hue
Solid content (wt%)	42.0 ± 1
pH	6.0–9.0
Viscosity (mPa.s)	1000–4000
Mechanical stability (2500rpm,0.5hr)	Pass
Minimum film forming temperature (°C)	23
Average particle size (μ m)	0.10–0.20
Ionicity	Anion

Application

- Real Stone Paint
Emulsion percentage in the formula: 12%–18% meet national standards of JG/T24–200.
- Color Sand Paint
- Application temperature: 5°C–40°C
Note: Do not apply before or right after rain. Ensure there is no free standing water on the substrate prior to application.

Packaging & storage

- Package: 1MT IBC tote or 20MT flexitank.
- Storage: the product should be kept away from sun light in a cool place; storage temperature is 5°C–35°C; storage time of efficacy is 6 months.

Safety information

Please refer to product MSDS.