

XL-788 Silicone Pure Acrylic Emulsion

Features

- Shell and nuclear silicone pure acrylic copolymer.
- High gloss,excellent anti-weathering performance,high dirt resistance.
- Good permeability,excellent water white resistance.

Product data

Appearance	Milky white liquid with blue hue
Solid content (wt%)	47.0 ± 1
pH	6.0-9.0
Viscosity (mPa.s)	1000-4000
Mechanical stability (2500rpm,0.5hr)	Pass
Minimum film forming temperature (°C)	17
Average particle size (μ m)	0.10-0.20
Ionicity	Anion

Application

- Top Coat
Emulsion percentage in the formula: 80%-100%.
- Application temperature: 5°C- 40°C
Note: Do not apply before or right after rain. Ensure there is no free standing water on the substrate prior to application.

Packaging & storage

- Package: 1MT IBC tote or 20MT flexitank.
- Storage: the product should be kept away from sun light in a cool place; storage temperature is 5°C-35°C; storage time of efficacy is 6 months.

Safety information

Please refer to product MSDS.