

CUB-510-45 Fiberglass Mesh Medium Soft Glue

FEATURES:

- Medium soft acrylic glue with excellent mesh yarn fixing performance.
- Coated mesh under oven temperature 135 °C in 2-3 minutes will cure and fix well
- High alkali aging tensile strength retaining rate and excellent waterproofing and alkali resistance

Product Data:

item	index
Appearance	Milky white Liquid with blue hue
Solid content (wt%)	45.0±1
PH	7.5-9.0
Viscosity (mpa. s)	500-2000
Mechanical stability (2500rpm, 0.5hr)	Pass
Tg(°C)	7
Particle Size, um	0.15-0.25
Ionicity	Anion

APPLICATION:

- Fiberglass mesh glue
- Immersive coating
- Could be mixed with CUB-542-45 to adjust the coating stiffness.

PACKAGING & STORAGE

1. Package: 1MT IBC tote or 22.8MT Flexitank.
2. Storage: the product should be kept away from sun light in a cool place; storage temperature is 5-35 °C; storage time of efficacy is 6 months.

SAFETY INFORMATION

Please refer to MSDS.

重要事项： 以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。