

浙江科力森化学有限公司 Zhejiang Cothanes Chemical Co., Ltd.

地址: 浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号 电话: 0575-82560088 82050581 传真: 0575-82051479

邮编: 312369 E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com

CUY-955 Pressure-sensitive Adhesive Emulsion (High Viscosity)

1. Product Introduction

CUY-955(High Viscosity) is a stable and especially sticky acrylate copolymer emulsion adhesive. It is suitable for the production of fabric adhesive tape, paper-based adhesive sticky tape, PVC adhesive tape, BOPP adhesive tape, self-adhesive fiberglass mesh tape and so on.

2. Product Features

CUY-955 is a stable and especially adhesive acrylate copolymer emulsion adhesive. The product has outstanding **Primary Adhesive**. And the product formula makes the cohesion and adhesion of resin reach a good balance over a long period of continuous experiments. The adhesive tape made by CUY-955 has good low-temperature adhesiveness and strong peeling strength.

3. Product specification

item	index
Solid content (wt%)	54.0 ± 1
PH	7. 0-9. 0
Viscosity (mpa. s, 1#60)	2000-2800
Tg, ℃	-40
Mechanical stability (2500rpm, 0.5hr)	Pass
Average particle size (μ m)	0. 3-0. 4
Ionicity	Anion

里安小贝: 以上资料供阁下参考,并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时,用户必须通过试验,制订最为适合的生产方法及控制测试,以确保产品的一致性及品质。 在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。



浙江科力森化学有限公司 Zhejiang Cothanes Chemical Co., Ltd.

地址: 浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号 电话: 0575-82560088 82050581 传真: 0575-82051479

E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com

4. Package and storage

1. Package: 50Kg plastic drum, 200Kg iron drum, 1000Kg plastic drum.

2. Storage: the product should be kept away from the light in a cool place; storage temperature is 5-35 $^{\circ}$ C; storage time of efficacy is 6 months.

5. Safety Info

Please refer to MSDS.

🚼 以上资料供阁下参考,并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前 或原料或施工环境有较大的改变时,用户必须通过试验,制订最为适合的生产方法及控制测试,以确保产品的一致性及品质。 在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。