

CUY-966G Pressure-sensitive Adhesive Emulsion

1. Product Introduction

CUY-966G is a stable and water based adhesive pure acrylic acetate copolymer emulsion (adhesive/glue). It is suitable for the production of fiberglass self-adhesive tape, suitable for making EPS decoration line & Roman Column.

2. Product Features

CUY-966G is a stable and strong adhesion acrylate copolymer emulsion adhesive. The product has very good **Primary Adhesive** and excellent **Lasting Adhesive** performance. And the product formulation makes the cohesion and adhesion of glue reach a good balance from our long period of R&D. The adhesive tape made by CUY-966G has good low-temperature adhesion performance and strong anti-peeling strength.

3. Product specification

item	index
Solid content (wt%) (1g glue, 20min/150°C)	54.0±1
PH	7.0-9.0
Viscosity (mpa. s)	200-1000
Tg(°C)	-40
Mechanical stability (2500rpm, 0.5hr)	Pass
Particle Size, um	0.2-0.3
Ionicity	Anion

4. Package and storage

1. Package: 1MT IBC tote, 22.8MT flexitank.
2. Storage: the product should be kept away from the light in a cool place; storage temperature is 5-35 °C; storage time of efficacy is 6 months.

5. Safety Info

Please refer to MSDS.

重要事项：以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。



COOTHANES
科力森

浙江科力森化学有限公司

Zhejiang Cothanes Chemical Co., Ltd.

地址：浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号
电话：0575-82560088 82050581 传真：0575-82051479
邮编：312369 E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com



重要事项：以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。