



## CU-2H Emulsion

### 1. Product Introduction

CU-2H is designed according to customers' special requirement for laminating products, which is applicable to advanced compound machine with a high degree of automation.

### 2. Product Features

CU-2H is self-crosslinking styrene acrylate emulsion resin which has good cohesion with fiber and polyurethane sponge, and has Strong waterproof and resistivity against water. Besides, it is easy to clean and the consumption is very economic.

We recommend setting the oven temperature at 135 °C, and drying for 2-3 minutes in oven. The drying temperature and time need to be adjusted by the machine running speed and local environment temperature.

### 3. Product specification

item	index
Solid content (wt%)	44.0±0.5
PH	3.0-6.0
Viscosity (mpa. s, 4#12)	6000-12000
Tg, °C	18
Average particle size (μ m)	0.1

### 4. Package and storage

1. Package: 50Kg plastic drum, 200Kg iron drum, 1000Kg IBC TOTE.
2. Storage: the product should be kept away from the light in a cool place; storage temperature is 5-35 °C; storage time of efficacy is 6 months.

**重要事项：**以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。