



XL-1345 Silicone Styrene Acrylic Emulsion

Features:

- Core-shell structure technology, Silicone modified Styrene Acrylic emulsion
- Fast drying, excellent water white performance and good anti-yellowing performance.
- Excellent dirt resistance, APOE & Formaldehyde free.

Product Data:

Appearance	Milky white with blue
Solid content, wt%	45.0±1
PH	7.5-9.0
Viscosity, mPa.s	1000-3000
Average particle size, μm	0.1
MFFT, °C	26
Ionicity	Anion

Application:

- Recommended to be used as natural stone paint emulsion.
- Suggested emulsion weight percentage in the paint formula: 30%-60%
- Application temperature: +5°C~40°C, do not apply when there's raining or will be raining.

Packaging & Storage:

- 1000KG IBC TOTE or 22.8MT Flexitank.
- The product should be kept away from the light in a cool place;
- Storage temperature is 5-35 °C; storage time of efficacy is 6 months.

Safety Information:

- Please refer to product MSDS.

重要事项：以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。