



## XL-777 Nature Stone Acrylic Emulsion

### Features:

- LIPN technology, Silicone modified Styrene Acrylic emulsion
- Fast drying, excellent water white performance and good anti-yellowing performance, excellent dirt resistance. Good film forming performance in high humidity and low temperature environment.
- APOE & Formaldehyde free, odor free emulsion.

### Product Data:

|                           |                       |
|---------------------------|-----------------------|
| Appearance                | Milky white with blue |
| Solid content, wt%        | 45.0±1                |
| PH                        | 7.0-9.0               |
| Viscosity, mPa.s          | 4000-10000            |
| Average particle size, μm | 0.1                   |
| Tg, °C                    | 29                    |
| MFFT, °C                  | 28                    |
| Ionicity                  | Anion                 |

### Application:

- Recommended to be used as natural stone paint emulsion.
- Suggested emulsion weight percentage in the paint formula: 30%-60%
- Application temperature: +5°C~40°C, do not apply when there's raining or will be raining.

### Packaging & Storage:

- 50KG PLASTIC DRUM, 1000KG IBC TOTE.
- The product should be kept away from the light in a cool place;
- Storage temperature is 5-35 °C; storage time of efficacy is 6 months.

### Safety Information:

**重要事项：**以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。



# 浙江科力森化学有限公司

## Zhejiang Cothanes Chemical Co., Ltd.

地址：浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号  
电话：0575-82560088 82050581 传真：0575-82051479  
邮编：312369 E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com

- Please refer to product MSDS.

### 重要事项：

以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。