



## XL-1200 Pure Acrylic Medium Soft Primer

### 1. Product Introduction

XL-1200 is a pure acrylic emulsion of good adhesion and fine particle which is used as interior & exterior primer to improve the quality of coating.

### 2. Product Features

XL-1200 has advantages of strong adhesion, fine particle, low viscosity and good permeability, low temperature application extends the painting season. It seals coated and uncoated porous surfaces. It has excellent water resistance, alkali resistance and chemical stability. This product is uniquely formulated to deliver long lasting protection for interior & exterior surfaces threatened by the elements, delivering extended maintenance cycles and long-term cost savings.

### 3. Product specification

item	index
Solid content (wt%)	30.0±1
PH	7.0-9.0
Viscosity (mpa. s)	<100
Calcium stability	Pass
Mechanical stability (2500rpm, 0.5hr)	Pass
Minimum film forming temperature(°C)	7
Tg, °C	16
Ionicity	Anion

### 4. Package and storage

1. Package: 1000Kg IBC TOTE
2. Storage: the product should be kept away from the light in a cool place; storage

**重要事项：**以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。



# 浙江科力森化学有限公司

## Zhejiang Cothanes Chemical Co., Ltd.

地址：浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号  
电话：0575-82560088 82050581 传真：0575-82051479  
邮编：312369 E-mail: zgf@xinlichemical.com Http://www.xinlichemical.com

temperature is 5-35 °C; storage time of efficacy is 6 months.



**重要事项：**以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。