

浙江科力森化学有限公司 Zhejiang Cothanes Chemical Co., Ltd.

地址:浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号 电话:0575-82560088 82050581 传真:0575-82051479 邮编:312369 E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com

XL-402 Waterproof Acrylic Emulsion

1. Product Introduction

XL-402 is anionic self-crosslinking emulsion which copolymers by styrene and acrylic monomer, which is used for two-component cement waterproof slurry and flexible two-component mortar.

2. Product Features

XL-402 is an Environmental friendly water based acrylic emulsion which has good compatibility with concrete. It can increase the intensity, cohesiveness, durability, flexibility, alkali resistance and water resistance of concrete and cement mortar and improve the brittleness of concrete. It also can improve the cohesiveness, compactness, anticorrosion, impact resistance and wear resistance.

3. Product specification

| item | index |
|----------------------------------------|--------------|
| Solid content (wt%) | 55.0 \pm 1 |
| РН | 7.0-9.0 |
| Viscosity (mpa. s) | 200–2500 |
| Tg, °C | -12 |
| Calcium stability | Pass |
| Mechanical stability (2500rpm, 0. 5hr) | Pass |
| Minimum film forming temperature(°C) | 0 |
| Average particle size (µm) | 0.3 |
| Surfactant type | Anion |

4. **Package and storage**

1. Package: 50kg Plastic Drum, 1MT IBC tote or 22.8MT Flexitank.

2. Storage: the product should be kept away from the light in a cool place; storage temperature is 5-35 °C; storage time of efficacy is 6 months.

重要事项: 以上资料供阁下参考,并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前 或原料或施工环境有较大的改变时,用户必须通过试验,制订最为适合的生产方法及控制测试,以确保产品的一致性及品质。 在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。