



# 浙江科力森化学有限公司

## Zhejiang Cothanes Chemical Co., Ltd.

地址：浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号  
电话：0575-82560088 82050581 传真：0575-82051479  
邮编：312369 E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com



# 浙江科力森化学有限公司

## Zhejiang Cothanes Chemical Co., Ltd.

地址：浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号  
电话：0086-0575-82110606 Mob: 0086-131-064-433-36  
邮编：312369 Email: frank@cothanes.com

## **XL-800A ELASTOMERIC EMULSION**

### **FEATURES:**

- **Excellent elasticity and flexibility**
- **APEO free, no formaldehyde & phenol, Environment friendly**
- **Very good anti-weathering performance, ultraviolet stability.**
- **Excellent resistance to chalking and yellowing. Excellent dirt pick-up resistance.**
- **Excellent adhesion when applied on various substrates and excellent waterproofing & alkali resistance.**
- **Excellent chemical stability, good compatibility with additives and pigments.**

### **Product Data:**

<b>item</b>	<b>index</b>
<b>Appearance</b>	<b>Milky white Liquid with blue</b>
<b>Solid content (wt%)</b>	<b>51.0±1</b>
<b>PH</b>	<b>7.0-9.0</b>
<b>Viscosity (mpa. s, 2#30 rpm)</b>	<b>&lt;1000</b>
<b>Mechanical stability (2500rpm, 0.5hr)</b>	<b>Pass</b>
<b>Tg (°C)</b>	<b>-7</b>
<b>Average particle size (µm)</b>	<b>0.15</b>
<b>Ionicity</b>	<b>Anion</b>

### **APPLICATION :**

- **Exterior Elastomeric Top Coating, Single Component Waterproofing Coating**
- **Roof insulating coating with small glass bead to reflect sun light away**
- **Application Temperature: 5°C- 35°C**
- **Applied thicknesses ranging from 10 to 30 mils**

### **PACKAGING & STORAGE**

1. **Package: 50kg drums, 1MT IBC tote or 22.8 Tons Flexitank.**
2. **Storage: the product should be kept away from sun light in a cool place; storage temperature is 5-35 °C; storage time of efficacy is 6 months.**

**重要事项：** 以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。



COOTHANES  
科力森

# 浙江科力森化学有限公司

## Zhejiang Cothanes Chemical Co., Ltd.

地址：浙江省绍兴市上虞区杭州湾上虞经济技术开发区纬七路12号  
电话：0575-82560088 82050581 传真：0575-82051479  
邮编：312369 E-mail:zgf@xinlichemical.com Http://www.xinlichemical.com



**重要事项：**以上资料供阁下参考，并不构成本公司承担用户产品质量及施工两责任的法律保证。在首次使用本产品前或原料或施工环境有较大的改变时，用户必须通过试验，制订最为适合的生产方法及控制测试，以确保产品的一致性及品质。在获知哪种应用及环境和生产条件后本公司可提供技术方面的建议。请向本公司代表询问上述细则。